

HY Networks (Shanghai) Co., Ltd.


Rm 408, Building A8, Taishang Innovation Park, No.428, Wubao Road, Minhang District, Shanghai, People's Republic of China Zip code: 201101 Tel: 86-21-5671 0796 Fax: 86-21-5671 0715

Technical Data Sheet

Code No: UPU4-145A

Description:

UHMWPE UD fabric is compounded by UHMWPE fiber with particular processes by our advanced high-tech equipment. It has the characters and superior performances such as high tensile strength, large modulus, soft texture, impact resistance, cutting resistance, high flexibility, acid & alkaline



resistance, sunshine proof, soaking proof and moisture proof. Because of the advantages, it is widely used in the applications like bullet proof vests, bullet proof helmets, bullet proof armor plates, stab proof and cutting proof clothes as well as special public anti-explosion facilities and safety protection facilities.

Technical data:

| Unit Weight | | 145 ± 5 g/m² | | |
|-------------------------------|--------|---------------------|------------|--|
| Yarn | | 800 Denier | | |
| Direction | | 0° /90° /0° /90° | | |
| Width | | 1.2m | | |
| Thickness | | 0.21 mm | | |
| Protection requirements | Layers | Product unit weight | Standard | |
| China Public Security Level 2 | 35 | 5.08kgs/m2 | GA141-2010 | |
| China Public Security Level 3 | 45 | 6.53kgs/m2 | GA141-2010 | |
| NIJ IIIA 9mm | 30 | 4.35kgs/m2 | NIJ0101.04 | |
| NIJ IIIA .44 | 38 | 5.51kgs/m2 | NIJ0101.06 | |

Yarn used: 800D/736F

| Physical Properties | Unit | Nominal | Result | Test Method |
|---------------------|---------|---------|--------|-------------|
| Count | dtex | / | 881 | GB/T14343 |
| Count CV | % | ±4.0 | -0.8 | |
| Breaking Tenacity | CN/dtex | ≥34.0 | 36.1 | |
| Modulus | CN/dtex | ≥1250 | 1670 | GB/T19975 |
| Breaking Elongation | % | ≤4.0 | 2.8 | |

www.hynetworks.com Email: info@hynetworks.com